


## TECHNICAL SPECIFICATIONS PROPLAY 35

| COMPOSITE  |             |                  |               |
|--|-------------|------------------|---------------|
| Description  | Value       |                  | Standard      |
| <b>Dimensions</b>  |             |                  |               |
| Minimum thickness (at a load of 2 kPa)   | 35          | mm               |               |
| Length x width (of pannels)  | 2.25 x 0.90 | m                |               |
| Due to influence of large temperature changes, the panels can expand and/or shrink during the installation.  |             |                  |               |
| <b>Mass per unit area</b>  | 3700        | g/m <sup>2</sup> |               |
| <b>Critical fall height</b>  | 1.3         | m                | EN 1177       |
| Resulting in a HIC value of 1000.  |             |                  |               |
| Single layer under 24 mm artificial grass with 25 kg/m <sup>2</sup> sand   | 1.7         | m                | EN 1177       |
| Double layer under 24 mm artificial grass with 25 kg/m <sup>2</sup> sand   | 2.7         | m                | EN 1177       |
| <b>Drainage</b>  |             |                  |               |
| In-plane water flow capacity (rigid/rigid), at i = 0.03 (and a load of 2 kPa)  | 0.06        | l/s.m            | EN-ISO 12958  |
| Permeability normal to the plane, without load; velocity index [V <sub>LH50</sub> ]  | 0.018       | m/s              | EN-ISO 11058  |
| Water infiltration rate [I <sub>A</sub> ]  | 5522        | mm/h             | EN 12616      |
| <b>Isolation</b>   |             |                  |               |
| Thermal conductivity [λ <sub>10</sub> ]  | 0.05        | W/m.K            | EN 12667      |
| <b>Durability</b>  |             |                  |               |
| Based on the available guidelines (according ISO/TR 13434), predicted to be durable for a minimum of 100 years.  |             |                  |               |
| microbiological resistance (according EN 12225) - resistance to: weathering (according EN 12224) - oxidation (according EN-ISO 13438) - acids & bases (according EN 14030) |             |                  |               |
| TEXTILE  |             |                  |               |
| Thermal bonded PET (Polyester)   |             |                  |               |
| Thickness  | 0.3         | mm               | EN-ISO 9073-2 |
| Mass per unit area   | 70          | g/m <sup>2</sup> | EN 29073-1    |
| Tensile strength (MD - CMD)  | 170 - 130   | N/50mm           | EN 29073-3    |
| FOAM   |             |                  |               |
| Thermal bonded 100% closed-celled PEX (cross-linked Polyethene)  |             |                  |               |
| Application range from -80 until +100 °C (melting range from +130 until +200 °C)   |             |                  |               |
|    |             |                  |               |
| All specifications are based on reports of independent laboratories and the knowledge of Schmitz Foam Products B.V. at the time of printing.                               |             |                  |               |
| Schmitz Foam Products B.V. reserves oneself the right of changing the specifications and/or the products.  |             |                  |               |
| E&OE   |             |                  |               |